

CONTRAFLAM® One 120 US/C

Fire Rated clear tempered interlayered safety glass for interior applications

Classification



Fire resistive
This glass product can withstand fire exposure to the non-fire side and protects from flames, smoke, radiant heat and hot gases.



Impact safety
Impact safety rated to meet the highest human impact safety ratings.



Hose Stream
This product has passed a hose stream test.

Available Options



→ Extra clear



→ Patterned glass



→ Double glazing

Contact us for a personalized solution to meet your product requirements.

Technical Specifications

HYBRIDCORE TECHNOLOGY™

Fire Rating		120 minutes
US / Canada Standards		UL 263; ASTM E119, E2226; CAN/ULC S101
Building code markings		W 120
Impact Safety Rating		ANSI Z97.1; CPSC 16CFR 1201-CAT II; CAN/CGSB - 12.1-M90
Application		Interior
Product		CONTRAFLAM® One 120 US/C
Glass Type		Planiclear Diamant
Nominal thickness		1-7/16 in. (37 mm) 1-7/16 in. (37 mm)
Thickness tolerance		± 5/64 in. (± 2 mm) ± 5/64 in. (± 2 mm)
Weight		12.1 lbs/sq. ft. (59 kg/ m²) 12.1 lbs/sq. ft. (59 kg/ m²)
STC/OITC rating (ASTM E 413/E1332)		41 / 41 measured 41 / 41 measured
Visible transmittance (NFRC 200)		87% 89%
Light reflection pL ext./int. (CIE 15)		8% / 8% 8% / 8%
U-factor (Btu/h*sq.ft*deg F) (NFRC 100)		Winter: 0.789 / Summer: 0.738 Winter: 0.789 / Summer: 0.738
Solar heat gain coefficient (NFRC 200)		0.68 0.71
Energy transmission (NFRC 300)		57% 61%
Non Loadbearing Wall Assemblies:		126-3/16 in. (3206mm); 126-3/16 in. (3206mm);
Max dimensions [Based on Intertek Spec ID 73711]		Area: 45.1 sq. ft. (4.19 m²) Area: 45.1 sq. ft. (4.19 m²)
Temperature range		-40°C / +60°C (-40°F / + 140 °F) -40°C / +60°C (-40°F / + 140 °F)

Additional Information to CONTRAFLAM 90-1
Exterior applications might be possible, please contact us.